

Fluorescent Whitening Agents For Cotton - 2						
Dazzle White	P Liq.	BVN	STA Liq.	2B	WHN	PC
Chemical Constitution	Stilbene Derivative	Stilbene Derivative	Stilbene Derivative	Stilbene Derivative	Stilbene Derivative	Stilbene Derivative
Appearance	Brownish Yellow Liq	Pale Yellow Pdr	Yellow Liq	Pale Yellow Pdr	Pale Yellow Pdr	Pale Yellow Pdr
pH Range	4.5 - 11	5.0 - 11	3.5 - 11	8.0 - 9	9.6 - 10	3.5 - 11
Ionic Nature	Anionic	Anionic	Anionic	Anionic	Anionic	Anionic
Solubility	Good	Good	Good	Good	Good	Good
Shelf Life	1 Year	Stable	1 Year	1 Year	1 Year	1 Year
Affinity	Medium	High	Low	High	High	High
Suitability	Cellulosic Fibres	Cellulosic Fibres	Cellulosic Fibres	Cellulosic Fibres	Wool / Silk / Polyamide	Wool / Silk / Polyamide
	(Exhaust / Padding Method)	(Exhaust Method)	(By Padding With resin) (DMDHEU)	(Exhaust Method)	(Exhaust Method)	(Exhaust Method)